



Europäisches Patentamt
European Patent Office
Office européen des brevets



(11)

EP 1 323 398 B1

(12)

EUROPEAN PATENT SPECIFICATION

(45) Date of publication and mention
of the grant of the patent:
14.06.2006 Bulletin 2006/24

(51) Int Cl.:
A61F 13/472 ^(2006.01) **A61F 13/15** ^(2006.01)

(21) Application number: **02028260.4**

(22) Date of filing: **16.12.2002**

(54) **Drapable absorbant article**

Drapierbarer absorbierender Artikel

Article absorbant drapable

(84) Designated Contracting States:
**AT BE BG CH CY CZ DE DK EE ES FI FR GB GR
IE IT LI LU MC NL PT SE SI SK TR**

(30) Priority: **19.12.2001 US 25299**

(43) Date of publication of application:
02.07.2003 Bulletin 2003/27

(73) Proprietor: **McNEIL-PPC, INC.
Skillman,
New Jersey 08558 (US)**

(72) Inventors:
• **Santos, Collado H.
Las Pinas City, 1740 (PH)**
• **Maria, Elaine P. de Velez
Quezon City (PH)**
• **Haarer, Jutta S.
Princeton, NJ 08540 (US)**
• **Ludwig, Barbara Ann
Basking Ridge, NJ 07920 (US)**

- **Marcelo, Ana Maria Elena R.
North Brunswick,
NJ 08902 (US)**
- **Moscherosch, Michael H.
Doylestown, PA 18901 (US)**
- **Pilate, Rita Renee
Washington Crossing, PA 18977 (US)**
- **Sturgeon, Jennifer L.
Long Valley, NJ 07853 (US)**

(74) Representative: **Metten, Karl-Heinz et al
Forrester & Boehmert,
Pettenkoferstrasse 20-22
80336 München (DE)**

(56) References cited:

EP-A- 0 685 214	EP-A- 0 705 583
EP-A- 1 029 522	EP-A- 1 108 406
WO-A-99/25290	US-A- 5 910 137
US-A- 6 114 595	US-B1- 6 177 605

Note: Within nine months from the publication of the mention of the grant of the European patent, any person may give notice to the European Patent Office of opposition to the European patent granted. Notice of opposition shall be filed in a written reasoned statement. It shall not be deemed to have been filed until the opposition fee has been paid. (Art. 99(1) European Patent Convention).

EP 1 323 398 B1

DescriptionField of the Invention

5 **[0001]** The invention relates to absorbent articles for use with undergarments or other clothing such as panty hose, swimsuits, or leotards. In particular, the absorbent articles of the present invention are drapeable.

Background of the Invention

10 **[0002]** Disposable absorbent articles such as, pantliners, sanitary napkins, interlabial devices, adult incontinence devices and diapers are well known in the art. These articles typically have a fluid permeable body-facing side and fluid impermeable garment facing side.. Additionally, such articles may include an absorbent layer for retaining fluids there-between.

15 **[0003]** Anatomical adaptation of an absorbent article may increase comfort to the wearer. That is, movement by the wearer may cause the absorbent article to conform to the geometry of the space between the wearer's thighs. In contrast, if the absorbent article is stiff to begin with, the wearer may experience discomfort and be conscious of the absorbent article. Additionally, if such an article bunches, there is a tendency to maintain its resulting distorted shape, thereby providing inadequate leakage protection.

20 **[0004]** Various methods have been used to improve the flexibility of absorbent articles. For example, reducing the amount of absorbent material, using less stiff resilient materials and using thinner materials have been disclosed as possible solutions to the improving the flexibility of absorbent articles. See, for example, PCT Application No. WO 98/09593 to Gilman, which purports to disclose a thin absorbent article that has a thickness of less than five millimeters and a crush recovery value of at least about fifteen mm.

25 **[0005]** EP 1077052 (Lariviere et al.) discloses using preferential bending zones extending along the longitudinal axis of an absorbent article together with a pair of longitudinal adhesive zones that register with the preferential bending zones to improve flexibility.

30 **[0006]** Another method that has been disclosed to improve flexibility is increasing the elasticity of the article. See, for example, US Patent No. 4,773,904 (Nakanishi et al.) and PCT Application No. WO 96/10978 (Palumbo et al.). In EP 0705583 and EP 0705586 (both to Querqui), the purported flexible absorbent article is disclosed as being elastically stretchable while having a water vapor permeable backsheet and a specific adhesive configuration.

35 **[0007]** Adding regions of corrugation have been disclosed as yet another method to increase flexibility or conformability of absorbent articles. EP 1088536 (Carvalho) discloses using longitudinal corrugations to provide lateral extensibility. Additionally, US Patent No. 5,607,415 (Datta et al.) purports to disclose an absorbent article having a basin-like moisture barrier with corrugations to provide an extendable region.

40 **[0008]** NZ 236101 (Hujber et al.) discloses a pants liner having a creped portion that attaches directly onto the crotch area of the wearer's pants. Parts of the liner is capable of being draped down the tubular leg portion of the pants, without any bunching or folding occurring in the creped portion of the liner.

45 **[0009]** However, the above absorbent articles are not fully flexible and do not adapt to the body as an undergarment alone does, thereby sacrificing comfort, protection and discretion. Thus, there is a need for a drapeable absorbent article that is fully flexible and adapts to the body as an undergarment alone does without sacrificing comfort, protection, and discretion. Applicants have surprisingly discovered such an absorbent article, which is described herein.

Summary of the Invention

50 **[0010]** The present invention is directed to an absorbent article having a silhouette including a first end, a second end, wherein the second end being in opposite relation to the first end, and a first longitudinally extending edge opposed to a second longitudinally extending edge, the first and second longitudinally extending edges connecting the first end and the second end; and a layered portion having a body-facing layer and a garment-facing layer, wherein the absorbent article is drapable.

55 **[0011]** In an alternate embodiment, the absorbent article also includes an absorbent layer and a transferlayer.

Detailed Description of the Invention

60 **[0012]** As used herein, the terms "drapeable" and "drapability" are used interchangeably and mean having a flexural resistance of about 30 g. or less as tested by the Modified Circular Bend Test, ASTM 4032-82 as set forth in the Example section below. It has been found that, for example, cotton underwear (e.g., Hanes Cotton underwear) has a flexural resistance of less than 30 g.

65 **[0013]** As used herein, all ranges provided are intended to expressly include at least all numbers that fall between the

endpoints of ranges.

[0014] Absorbent articles of this invention have three portions: an anterior portion, a central portion, and a posterior portion and at least a body-facing layer and a garment facing layer. Any sample of the present invention taken from any portion of the entire article that includes all of the layers of the finished product is drapeable.

[0015] In one embodiment of the present invention, the absorbent article has a body facing layer and a garment facing layer. In another embodiment, the absorbent article additionally includes an absorbent layer therebetween. Other embodiments may include additional layers such as, a transfer or distribution layer, multiple layer absorbent layers and unitized versions of two or more layers.

[0016] The silhouette of absorbent articles of this invention includes those designed to fit undergarments having conventionally-shaped crotches. Additionally, absorbent articles of the present invention may also be designed to fit undergarments having abbreviated crotches including those of thong underwear, string underwear, G-string type underwear, Rio cut underwear, Brazilian cut underwear, etc. Absorbent articles of this invention may or may not include wings, flaps or tabs for securing the absorbent article to an undergarment.

[0017] The absorbent article of the present invention includes a liquid permeable layer also referred to as a body facing layer. The exterior of the body facing layer forms the body-facing surface of the absorbent article. The body facing layer may be a single layer or be made from multiple layers. The body facing layer may be formed from any fluid pervious material or combinations of materials that are comfortable against the skin and permits fluid to penetrate.. For instance, the body facing layer may be a fibrous non-woven fabric made of fibers or filaments of polymers, such as polyethylene, polypropylene, polyester, or cellulose, and combinations thereof. Alternatively, the body facing layer may be formed from an apertured polymeric film. The thickness of the body facing layer may vary from about 0.001 inch (0.025 mm) to about 0.200 inch (5.000 mm), depending on the material chosen. The weight of the body facing layer material is between about 5 to about 150 gsm.

[0018] For example, any material with cloth-like features may be used for the body facing layer. Such material include nonwoven materials, such as spunlace material, and woven materials. In particular, spunlace material made from the range of from 10 to 65% rayon and 35 to 90% polyester may be used.

[0019] In one embodiment, the body facing layer is a single sheet of material having a width sufficient to form the body-facing surface of the absorbent article. In another embodiment, the body facing layer has at least two layers.

[0020] The body facing layer, whether a single layer or multiple layers, may have absorbent capabilities, i.e., retains fluid. If a separate absorbent layer is used, the body facing layer may be longer and wider than the absorbent core or be of similar size as the absorbent core.

[0021] The garment facing layer of the present invention may be pliant and is typically referred to as a backsheet or barrier layer. The exterior of the garment facing layer forms the garment-facing surface of the absorbent article and, typically, is impermeable to fluids. In one embodiment, the garment facing layer may be any thin, flexible, fluid impermeable material, such as a polymeric film, e.g., polyethylene, polypropylene, or cellophane, or a normally fluid pervious material that has been treated to be impervious, such as impregnated fluid repellent paper or non-woven material, including non-woven fabric material, or a flexible foam, such as polyurethane or cross-linked polyethylene.

[0022] Additionally, the garment facing layer may be breathable, i.e., permits vapor to transpire. Known materials for this purpose include nonwoven materials and microporous films in which microporosity is created by, inter alia, stretching an oriented film. Single or multiple layers of permeable films, fabrics, melt-blown materials, and combinations thereof that provide a tortuous path, and/or whose surface characteristics provide a liquid surface repellent to the penetration of liquids may also be used to provide a breathable backsheet.

[0023] The thickness of the backsheet when formed from a polymeric film typically is about 0.001 inch (0.025 mm) to about 0.002 inch (0.051 mm).

[0024] One embodiment of the present invention includes an absorbent layer, which may be a single layer or, alternately, be made of multiple layers. Absorbent materials used in the absorbent layer may include, but are not limited to, absorbent fibers, such as cellulose fibers, including, but not limited to wood pulp, regenerated cellulose fibers, and cotton fibers, rayon fibers and the like; superabsorbent fibers or particles; other naturally occurring absorbent materials, such as peat moss; and other synthetic absorbent materials, such as foams and the like. The absorbent layer may also include one or more of the following: thermoplastic binder fibers, latex binder, perfumes, or odor-controlling compounds or compositions. The absorbent layer may be compressed or uncompressed, embossed, or calendered. Additionally, the absorbent core may be made from any known absorbent bicomponent fibers, including those made, for example, from polyester, polyethylene, polypropylene and any combinations thereof.

[0025] The absorbent material may be woven or nonwoven and made by any process known in the art. For example the absorbent material may be wet laid, carded, or air laid.

[0026] Wings, also called, among other things, flaps or tabs, and their use in sanitary protection articles is described in U.S. Patent. No. 4,687,478 to Van Tilburg; U.S. Patent No. 4,589,876 also to Van Tilburg, U.S. Patent No. 4,900,320 to McCoy, and U.S. Patent No. 4,608,047 to Mattingly. The disclosures of these patents are incorporated herein by reference in their entirety. As disclosed in the above documents, wings are generally speaking flexible and configured

to be folded over the edges of the underwear so that the wings are disposed between the edges of the underwear.

[0027] The shape of the wings may also be varied as desired. The wings may be rounded, rectangular, curvilinear, etc. The wings may be regular or irregular, symmetric or asymmetric in shape.

[0028] The overall dimensions of the absorbent article of the present invention may be as follows: a length of about 5 inches (127 mm) to 8 inches (203 mm) and a thickness of about 0.02 inch (0.5 mm) to 0.2 inch (5 mm).

[0029] Optionally, the absorbent article of the present invention may include a transfer or distribution layer. If included in the absorbent article, the transfer layer may be made of any known material that will take up fluid and then distribute and release it to an adjacent absorbent layer for storage. Transfer layers have a relatively open structure that allows for movement of fluid within the layer. Suitable materials for such transfer layers include fibrous webs, resilient foams, and the like.

[0030] The mass of materials making up the transfer layer may be absorbent, although the materials themselves are not absorbent. Thus, transfer layers that are made of hydrophobic, nonabsorbent fibers may be able to accept large volumes of fluid into interfiber void spaces while the fibers themselves do not absorb any significant quantities of fluid. Likewise, open-celled foam structures that are made from nonabsorbent materials may also absorb fluid into the cells of the foam. The walls of the cells, however, do not absorb any fluid. The cumulative spaces within the transfer layer, i.e., the interfiber void spaces in the fibrous transfer layer or the open cells in the foam transfer layer, function much like a container to hold fluid.

[0031] Typically, transfer layer fibrous webs are made of resilient, nonabsorbent materials to provide void volume and to allow for free movement of fluid through the structure. Transfer layers that are made from webs of mostly absorbent fibers absorb the fluid as it enters the structure and do not distribute it throughout the rest of the structure as efficiently as webs containing non-absorbent materials.

[0032] Adhesive is typically used to attach the layers into a single absorbent article. For example, in one embodiment, the body facing layer is attached to the barrier with adhesive HL 1491 available from H.B Fuller and Company (St. Paul, MN). The adhesive may be applied in any method.

[0033] Adhesive may also be applied to the garment facing side of the absorbent article. For example, pressure sensitive adhesive strips, swirls, or waves may be applied to help maintain the absorbent article in place. As used herein, the term pressure-sensitive adhesive refers to any releasable adhesive or releasable tenacious means. Suitable adhesive compositions, include, for example, water-based pressure-sensitive adhesives such as acrylate adhesives. Alternatively, the adhesive composition may include adhesives based on the following: emulsion or solvent-borne adhesives of natural or synthetic polyisoprene, styrene-butadiene, or polyacrylate, vinyl acetate copolymer or combinations thereof; hot melt adhesives based on suitable block copolymers - suitable block copolymers for use in the invention include linear or radial co-polymer structures having the formula $(A-B)_x$ wherein block A is a polyvinylarene block, block B is a poly(monoalkenyl) block, x denotes the number of polymeric arms, and wherein x is an integer greater than or equal to one. Suitable block A polyvinylarenes include, but are not limited to Polystyrene, Polyalpha-methylstyrene, Polyvinyltoluene, and combinations thereof. Suitable Block B poly(monoalkenyl) blocks include, but are not limited to conjugated diene elastomers such as for example polybutadiene or polyisoprene or hydrogenated elastomers such as ethylene butylene or ethylene propylene or polyisobutylene, or combinations thereof. Commercial examples of these types of block copolymers include Kraton™ elastomers from Shell Chemical Company, Vector™ elastomers from Dexco, Solprene™ from Enichem Elastomers and Stereon™ from Firestone Tire & Rubber Co.; hot melt adhesive based on olefin polymers and copolymers where in the olefin polymer is a terpolymer of ethylene and a co-monomers, such as vinyl acetate, acrylic acid, methacrylic acid, ethyl acrylate, methyl acrylate, n-butyl acrylate vinyl silane or maleic anhydride. Commercial examples of these types of polymers include Ateva(polymers from AT plastics), Nucrel(polymers from DuPont), Escor (from Exxon Chemical).

[0034] Also useful in attaching absorbent articles of the present invention to the crotch of undergarments are mechanical attachment means, e.g., clips, laces, ties, and interlocking devices, e.g., snaps, buttons, VELCRO (Velcro USA, Inc., Manchester, NH), zipper, and the like.

[0035] The absorbent article may be applied to the crotch of the undergarment or pants by placing the garment-facing surface against the inside surface of the crotch of the garment.

[0036] A release strip may be applied to protect adhesive on the absorbent article prior to attaching the absorbent article to the crotch of an undergarment. The release strip can be formed from any suitable sheet-like material adheres with sufficient tenacity to the adhesive to remain in place prior to use but which can be readily removed when the absorbent article is to be used. Optionally, a coating may be applied to release strip to improve the ease of removability of the release strip from the adhesive. Any coating capable of achieving this result may be used, e.g., silicone.

[0037] Any or all of the cover, absorbent layer, transfer layer, backsheet layer, and adhesive layers may be colored. Such coloring includes, but is not limited to, white, black, red, yellow, blue, orange, green, violet, and mixtures thereof. Color may be imparted according the present invention though dyeing and/or pigmentation. Colorants used according the present invention include dyes and inorganic and organic pigments. The dyes include, but are not limited to, Azo dyes (e.g., Solvent Yellow 14, Disperse Yellow 23, Metanil Yellow), anthraquinone dyes (Solvent Red 111, Disperse

Violet 1, Solvent Blue 56, and Solvent Green 3), Xanthene dyes (Solvent Green 4, Acid Red 52, Basic Red 1, and Solvent Orange 63), azine dyes (Jet black), and the like.

[0038] Inorganic pigments include, but are not limited to, titanium dioxide (white), carbon black (black), iron oxides (red, yellow, and brown), chromium oxide (green), ferric ammonium ferrocyanide (blue), and the like.

[0039] Organic pigments include, but are not limited to diarylide yellow AAOA (Pigment Yellow 12), diarylide yellow AAOT (Pigment Yellow 14), phthalocyanine blue (Pigment Blue 15), lithol red (Pigment Red 49:1), Red Lake C (Pigment Red), and the like.

[0040] The absorbent article may include other known materials, layers, and additives, such as, foam, net-like material, perfumes, medicaments or pharmaceutical agents, moisturizers, odor control agents, and the like. The absorbent article can optionally be embossed with decorative designs.

[0041] The absorbent article may be packaged as unwrapped absorbent articles within a carton, box or bag. The consumer withdraws the ready-to-use article as needed. The absorbent article may also be individually packaged (each absorbent article encased within an overwrap).

[0042] Also contemplated herein include symmetrical absorbent articles having parallel longitudinal edges, dog bone- or peanut-shaped, and the like.

[0043] From the foregoing description, one skilled in the art can ascertain the essential characteristics of this invention, and without departing from the spirit and scope thereof, can make various changes and modifications. Embodiments set forth by way of illustration are not intended as limitations on the variations possible in practicing the present invention.

EXAMPLE

[0044] Samples of commercially available pantliners were compared to samples of the present invention and samples from the crotch portion of an undergarment.

[0045] Peak bending stiffness is determined by a test that is modeled after the ASTM D 4032-82 CIRCULAR BEND PROCEDURE, the procedure being considerably modified and performed as follows. The CIRCULAR BEND PROCEDURE is a simultaneous multi-directional deformation of a material in which one face of a specimen becomes concave and the other face becomes convex. The CIRCULAR BEND PROCEDURE gives a force value related to flexural resistance, simultaneously averaging stiffness in all directions.

[0046] The apparatus necessary for the CIRCULAR BEND PROCEDURE is a modified Circular Bend Stiffness Tester, having the following parts:

1. A smooth-polished steel plate platform, which is 102.0 mm by 102.0 by 6.35 mm having an 18.75 mm diameter orifice. The lap edge of the orifice should be at a 45 degree angle to a depth of 4.75 mm;
2. A plunger having an overall length of 72.2 mm, a diameter of 6.25 mm, a ball nose having a radius of 2.97 mm and a needle-point extending 0.88 mm therefrom having a 0.33 mm base diameter and a point having a radius of less than 0.5 mm, the plunger being mounted concentric with the orifice and having equal clearance on all sides. Note that the needle-point is merely to prevent lateral movement of the test specimen during testing. Therefore, if the needle-point significantly adversely affects the test specimen (for example, punctures an inflatable structure), than the needle-point should not be used. The bottom of the plunger should be set well above the top of the orifice plate. From this position, the downward stroke of the ball nose is to the exact bottom of the plate orifice;
3. A force-measurement gauge and more specifically an Instron inverted compression load cell. The load cell has a load range of from about 0.0 to about 2000.0 g;
4. An actuator and more specifically the Instron Model No. 1122 having an inverted compression load cell. The Instron 1122 is made by the Instron Engineering Corporation, Canton, Mass.

[0047] In order to perform the procedure for this test, as explained below, five representative samples for each article are necessary. From each of the five samples to be tested, some number "Y" of 37.5 mm by 37.5 mm test specimens are cut. For undergarments, the crotch portion was made from at least one layer. For absorbent articles, test specimens were cut from anterior portion, the central portion, and the posterior portion. This test is directed to the overall drapeability of the article and not merely the peripheral portions thereof and, therefore, the drapeability of the present invention is more concerned with the drapeability of the entire article than any specific portion thereof.

[0048] The test specimens should not be folded or bent by the test person, and the handling of specimens must be kept to a minimum and to the edges to avoid affecting flexural-resistance properties.

[0049] The procedure for the CIRCULAR BEND PROCEDURE is as follows. The specimens are conditioned by leaving them in a room that is 21 °C, +/- 0.1 °C. and 50%, +/- 2.0%, relative humidity for a period of two hours. The plunger speed is set at 50.0 cm per minute per full stroke length. A specimen is centered on the orifice platform below the plunger such that the body facing layer of the specimen is facing the plunger and the barrier layer of the specimen is facing the platform. The indicator zero is checked and adjusted, if necessary. The plunger is actuated. Touching the specimen during the

EP 1 323 398 B1

testing should be avoided. The maximum force reading to the nearest gram is recorded. The above steps are repeated until all of the specimens have been tested.

CALCULATIONS

[0050] The peak bending stiffness for each specimen is the maximum force reading for that specimen. Remember that "Y" number of sets of five samples were cut. The values received for each specimen were averaged. The flexural resistance for an article is the average peak bending stiffnesses for all "Y" specimens taken from each sample of that article.

Table 1

Sample Number	Average Peak Load (grams)	Percent Standard Deviation
Commercially Available Underwear Sample 1	2.17	8.91
Commercially Available Underwear Sample 2	2.83	12.37
Commercially Available Underwear Sample 3	4.78	30.57
Inventive Sample 1	17.07	10.8
Inventive Sample 2	17.56	8.00
Inventive Sample 3	27.58	18.5
Comparative Sample 1	46.21	12.8
Comparative Sample 2	49.56	7.9
Comparative Sample 3	127.02	14.1
Comparative Sample 4	150.87	9.1
Comparative Sample 5	173.26	8.2
Comparative Sample 6	256.58	7.9
Comparative Sample 7	286.72	9.1

Commercially Available Underwear Sample 1 Hanes Her Way 100% Nylon with 100% Cotton Crotch (Grey) This article had two crotch layers, one was nylon and body-facing layer was cotton, which were not bonded together. Only the body-facing layer was tested.

Commercially Available Underwear Sample 2 Hanes Her Way 100% Nylon (black) ribbed crotch. This article had one crotch layer.

Commercially Available Underwear Sample 3 Fruit of the Loom 100% cotton jersey (cream colored). This article had two crotch layers, both were cotton. Only layer was tested. Inventive Sample 1 having a 75 gsm spunlace body facing layer made from 75% polyester and 25% rayon (3P075V25P75 from Spuntech Industries Ltd., Upper Tiberias, Israel) and a 30 gsm microporous polyethylene backsheet (01030A1-1-1-1-2, FullSafe, Manila, Philippines).

Inventive Sample 2 having a 75 gsm spunlace body facing layer made from 75% polyester and 25% rayon (LBN040, from PGI, Benson, NC) and a 30 gsm microporous polyethylene backsheet (01030A1-1-1-1-2, FullSafe, Manila, Philippines).

Inventive Sample 3 having a 75 gsm spunlace body facing layer made from 75% polyester and 25% rayon (LIDRO 356355 - Jacob Holm Industries S.A.S, Soultz, France), and absorbent core made from three layers (first layer: 10 gsm 100% PET/PE, second layer: 15 gsm 66% PET/PE/34% rayon and third layer: 15 gsm 66 PET/PE/34% rayon) (JS40-1, Kang Na Hsiung Enterprise Company, Ltd., Taipei, Taiwan), and a 30 gsm microporous polyethylene backsheet (01030A1-1-1-1-2, FullSafe, Manila, Philippines).

Comparative Samples 1-7 were samples of pantliners commercially available.

Sample number	Commercial Product Name (date code)
---------------	-------------------------------------

Comparative Sample 1	Sofy Regular Pantliner
Comparative Sample 2	Sofy Breathable (00120702123)
Comparative Sample 3	Kotex Lightdays (LF101002C)
Comparative Sample 4	Carefree Ultrathins

Table continued

Sample number	Commercial Product Name (date code)
Comparative Sample 5	Carefree Body Shape (1996M02341)
Comparative Sample 6	Carefree (Europe) (1057A)
Comparative Sample 7	Procter & Gamble Alldays Freshweave (0344CA11762040B)

Claims**1.** An absorbent article comprising

A. a silhouette comprising

- (i) a first end,
- (ii) a second end, wherein the second end being in opposite relation to the first end, and
- (iii) a first longitudinally extending edge opposed to a second longitudinally extending edge, the first and second longitudinally extending edges connecting the first end and the second end;

B. a layered portion comprising

- (i) a body-facing layer comprising a spunlace material including from about 10 to about 65 wt% rayon and from about 35 to about 90 wt% polyester,
- (ii) a garment facing layer;

wherein the absorbent article has a flexural resistance of less than 30 g.

2. The absorbent article of claim 1, wherein the body-facing layer comprises at least two layers.**3.** The absorbent article of claim 2, wherein the first layer forms a body facing surface and the second layer is absorbent.**4.** The absorbent article of claim 3, wherein the first layer comprises a spunlace material including from about 10 to about 65 wt% rayon and from about 35 to about 90 wt% polyester.**5.** The absorbent article of any of the previous claims, wherein the body-facing layer is absorbent.**6.** The absorbent article of any of the previous claims, further comprising an absorbent layer.**7.** The absorbent article of any of the previous claims, further comprising a transfer layer,**8.** The absorbent article of any of the previous claims, wherein the body-facing layer further comprises polyethylene.**9.** The absorbent article of any of the previous claims, wherein the article is selected from the group consisting of a pantliner, a sanitary napkin and an incontinence device.**10.** The absorbent article of any of the previous claims, further comprising at least one wing extending from the first longitudinal edge or the second longitudinal edge.**11.** The absorbent article of any of the previous claims, wherein the silhouette is shaped to fit within the crotch of a thong.**12.** The absorbent article of claim 11, further comprising at least one wing extending from the first longitudinal edge or the second longitudinal edge.**13.** The absorbent article of claim 1, wherein the layered portion comprises

- (i) a body-facing layer comprising a spunlace material including about 75 % polyester and about 25 % rayon, and
- (ii) a garment-facing layer comprising microporous polyethylene.

14. The absorbent article of claim 13, wherein the layered portion comprises

- (i) a body-facing layer comprising a spunlayce material including about 75 % polyester and about 25 % rayon,
- (ii) an absorbent layer comprising at least three layers, wherein the first layer comprises polyester and polyethylene, the second layer comprises polyester, polyethylene, and rayon, and the third layer comprises polyester, polyethylene, and rayon, and
- (iii) a garment-facing layer comprising micoporous polyethylene.

Patentansprüche

1. Absorbierendes Produkt, das Folgendes umfasst:

A. einen Umriss, der Folgendes umfasst:

- (i) ein erstes Ende,
- (ii) ein zweites Ende, wobei das zweite Ende sich in einer entgegengesetzten Beziehung zu dem ersten Ende befindet, und
- (iii) einen ersten sich längs erstreckenden Rand, der einem zweiten sich längs erstreckenden Rand entgegengesetzt ist, wobei die ersten und zweiten sich längs erstreckenden Ränder das erste Ende und das zweite Ende verbinden;

B. einen geschichteten Teilbereich, der Folgendes umfasst:

- (i) eine dem Körper zugewandte Schicht, die ein Spunlace-Material umfasst, das ungefähr 10 bis ungefähr 65 Gew.-% Rayon und ungefähr 35 bis ungefähr 90 Gew.-% Polyester einschließt,
- (ii) eine der Kleidung zugewandte Schicht;

wobei das absorbierende Produkt eine Biegezugfestigkeit von weniger als 30 g aufweist.

2. Absorbierendes Produkt nach Anspruch 1, wobei die dem Körper zugewandte Schicht mindestens zwei Schichten umfasst.

3. Absorbierendes Produkt nach Anspruch 2, wobei die erste Schicht eine dem Körper zugewandte Oberfläche bildet und die zweite Schicht absorbierend ist.

4. Absorbierendes Produkt nach Anspruch 3, wobei die erste Schicht ein Spunlace-Material umfasst, das ungefähr 10 bis ungefähr 65 Gew.-% Rayon und ungefähr 35 bis ungefähr 90 Gew.-% Polyester einschließt.

5. Absorbierendes Produkt nach einem der vorangehenden Ansprüche, wobei die dem Körper zugewandte Schicht absorbierend ist.

6. Absorbierendes Produkt nach einem der vorangehenden Ansprüche, das weiterhin eine absorbierende Schicht umfasst.

7. Absorbierendes Produkt nach einem der vorangehenden Ansprüche, das weiterhin eine Transferschicht umfasst.

8. Absorbierendes Produkt nach einem der vorangehenden Ansprüche, wobei die dem Körper zugewandte Schicht weiterhin Polyethylen umfasst.

9. Absorbierendes Produkt nach einem der vorangehenden Ansprüche, wobei das Produkt ausgewählt ist aus der Gruppe, bestehend aus einer Slipeinlage, einer Damenbinde und einer Inkontinenzvorrichtung.

10. Absorbierendes Produkt nach einem der vorangehenden Ansprüche, das weiterhin mindestens einen Flügel umfasst, der sich von dem ersten längslaufenden Rand oder dem zweiten längslaufenden Rand erstreckt.

11. Absorbierendes Produkt nach einem der vorangehenden Ansprüche, wobei der Umriss geformt ist, um in den Schritt

eines Tangas zu passen.

12. Absorbierendes Produkt nach Anspruch 11, das weiterhin mindestens einen Flügel umfasst, der sich von dem ersten längslaufenden Rand oder dem zweiten längslaufenden Rand erstreckt.

13. Absorbierendes Produkt nach Anspruch 1, wobei der geschichtete Teilbereich Folgendes umfasst:

- (i) eine dem Körper zugewandte Schicht, die ein Spunlace-Material umfasst, das ungefähr 75 % Polyester und ungefähr 25 % Rayon einschließt, und
- (ii) eine der Kleidung zugewandte Schicht, die mikroporiges Polyethylen umfasst.

14. Absorbierendes Produkt nach Anspruch 13, wobei der geschichtete Teilbereich Folgendes umfasst:

- (i) eine dem Körper zugewandte Schicht, die ein Spunlace-Material umfasst, das ungefähr 75 % Polyester und ungefähr 25 % Rayon einschließt,
- (ii) eine absorbierende Schicht, die mindestens 3 Schichten umfasst, wobei die erste Schicht Polyester und Polyethylen umfasst, die zweite Schicht Polyester, Polyethylen und Rayon umfasst, und die dritte Schicht Polyester, Polyethylen und Rayon umfasst, und
- (iii) eine der Kleidung zugewandte Schicht, die mikroporiges Polyethylen umfasst.

Revendications

1. Article absorbant, comprenant :

A. une silhouette comprenant :

- (i) une première extrémité,
- (ii) une seconde extrémité, dans laquelle la seconde extrémité est en relation opposée à la première extrémité, et
- (iii) un premier bord s'étendant de manière longitudinale opposé à un second bord s'étendant de manière longitudinale, les premier et second bords s'étendant de manière longitudinale raccordant la première extrémité et la seconde extrémité ;

B. une partie en couches, comprenant :

- (i) une couche orientée vers le corps comprenant un matériau non tissé lacé par filage comprenant d'environ 10 à environ 65% en poids de rayonne et d'environ 35 à 90% en poids de polyester,
- (ii) une couche orientée vers le vêtement ;

dans laquelle l'article absorbant a une résistance à la flexion inférieure à 30 g.

2. Article absorbant selon la revendication 1, dans lequel la couche orientée vers le corps comprend au moins deux couches.

3. Article absorbant selon la revendication 2, dans lequel la première couche forme une surface orientée vers le corps et la seconde couche est absorbante.

4. Article absorbant selon la revendication 3, dans lequel la première couche comprend un matériau non tissé lacé par filage comprenant d'environ 10 à environ 65% en poids de rayonne et d'environ 35 à environ 90% en poids de polyester.

5. Article absorbant selon l'une quelconque des revendications précédentes, dans lequel la couche orientée vers le corps est absorbante.

6. Article absorbant selon l'une quelconque des revendications précédentes, comprenant en outre une couche absorbante.

EP 1 323 398 B1

7. Article absorbant selon l'une quelconque des revendications précédentes, comprenant en outre une couche de transfert.

5 8. Article absorbant selon l'une quelconque des revendications précédentes, dans lequel la couche orientée vers le corps comprend en outre du polyéthylène.

9. Article absorbant selon l'une quelconque des revendications précédentes, dans lequel l'article est choisi dans le groupe comprenant un protège-slip, une serviette hygiénique et un dispositif contre l'incontinence.

10 10. Article absorbant selon l'une quelconque des revendications précédentes, comprenant en outre au moins une aile s'étendant à partir du premier bord longitudinal ou du second bord longitudinal.

11. Article absorbant selon l'une quelconque des revendications précédentes, dans lequel la silhouette est formée pour s'adapter dans l'entrejambe d'un tanga.

12. Article absorbant selon la revendication 11 précédentes, comprenant en outre au moins une aile s'étendant à partir du premier bord longitudinal ou du second bord longitudinal.

13. Article absorbant selon la revendication 1, dans lequel la partie en couches comprend :

(i) une couche orientée vers le corps comprenant un matériau non tissé lacé par filage comprenant environ 75% de polyester et environ 25% de rayonne, et

(ii) une couche orientée vers le vêtement comprenant du polyéthylène microporeux.

14. Article absorbant selon la revendication 13, dans lequel la partie en couches comprend :

(i) une couche orientée vers le corps comprenant un matériau non tissé lacé par filage comprenant environ 75% de polyester et environ 25% de rayonne,

(ii) une couche absorbante comprenant au moins trois couches, dans laquelle la première couche comprend du polyester et du polyéthylène, la seconde couche comprend du polyester, du polyéthylène et de la rayonne, et la troisième couche comprend du polyester, du polyéthylène et de la rayonne, et

(iii) une couche orientée vers le vêtement comprenant du polyéthylène microporeux.